

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 07-022227

(43)Date of publication of application : 24.01.1995

(51)Int.Cl. H01F 1/08

C22C 33/02

C22C 38/00

(21)Application number : 05-300773 (71)Applicant : TOSHIBA CORP

(22)Date of filing : 08.11.1993 (72)Inventor : TSUDAI AKIHIKO
SAKAI ISAO
MIZOGUCHI TETSUHIKO
INOMATA KOICHIRO

(54) PRODUCTION OF PERMANENT MAGNET

(57)Abstract:

PURPOSE: To produce a permanent magnet having high coercive force and high maximum energy product with high productivity by employing a permanent magnet alloy, having a specific composition of R, boron, gallium and the remainder principally comprising iron, as a starting material and then crushing, pressing under magnetic field, and sintering the alloy.

CONSTITUTION: A permanent magnet alloy composed of 10-40wt.% of R (R represents at least one element selected from Y and rare earth elements), 0.1-8wt.% of boron, 13wt.% or less of gallium, and the remainder mainly comprising iron is employed as a starting material. 30wt.% or less of Co is also added to the permanent magnet alloy. 90wt.% or less of Ga is substituted by Al. The magnet alloy thus obtained (oxygen concentration is 0.05-0.03wt.%) is crushed roughly in Ar atmosphere and then crushed finely by a jet mill. The fine powder is filled in a predetermined die and

compression molded while applying magnetic field and then it is sintered in Ar atmosphere before it is subjected to aging in vacuum at 550–750° C.

LEGAL STATUS

[Date of request for examination]	08.11.1993
[Date of sending the examiner's decision of rejection]	21.11.1997
[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]	
[Date of final disposal for application]	
[Patent number]	2868062
[Date of registration]	25.12.1998
[Number of appeal against examiner's decision of rejection]	09-21321
[Date of requesting appeal against examiner's decision of rejection]	18.12.1997
[Date of extinction of right]	

Copyright (C); 1998,2003 Japan Patent Office